

SUPPORTING INFORMATION for

Visualizing Nanostructures in Supramolecular Hydrogels: A Correlative Study Using Confocal and Cryogenic Scanning Electron Microscopy

Shaun M. Smith¹, Ferdinando Malagrecia¹, Jacqueline Hicks², Giuseppe Mantovani³, David B. Amabilino^{*4}, Christopher Parmenter^{2,3} and Lluïsa Pérez-García^{5,6}

Addresses:

¹ School of Chemistry, GSK Carbon Neutral Laboratories for Sustainable Chemistry, University of Nottingham, Triumph Road, NG7 2TU, United Kingdom.

² Nanoscale and Microscale Research Centre (nmRC), Cripps South Building (Building 53), University Park, NG7 2RD, United Kingdom

³ University of Nottingham, School of Pharmacy, NG7 2RD, United Kingdom.

⁴ Institut de Ciència de Materials de Barcelona (ICMAB-CSIC), Carrer dels Til·lers, Bellaterra, 08193 Spain.

⁵ Departament de Farmacologia, Toxicologia i Química Terapèutica, Facultat de Farmàcia i Ciències de l'Alimentació, Avda. Joan XXIII 27-31, Universitat de Barcelona, 08028 Barcelona, Spain

⁶ Institut de Nanociència i Nanotecnologia IN2UB, Universitat de Barcelona, Barcelona, 08028 Spain

Email: David Amabilino – amabilino@icmab.es

* Corresponding author

Table of Contents

1. Supplementary Figures
2. Supplementary Table

1. Supplementary Figures

Figure S1.




Figure S1. Plot displaying the absorption spectrum of DPP-BC in 1:1 water-ethanol solution, [DPP-BC] = 100 μ M (blue solid line), absorption spectrum of DPP-BC@Gel, [DPP-BC] = 200 μ M (red solid line), fluorescence emission spectrum of DPP-BC in 1:1 water-ethanol, [DPP-BC] = 100 μ M (blue dotted line), and fluorescence emission spectrum of DPP-BC@Gel, [DPP-BC] = 200 μ M (red dotted line). λ_{exc} = 530 nm for both fluorescence emission measurements.

Figure S2




Figure S2. Plot displaying the absorption spectrum of ZnPc in 1:1 water-ethanol solution, [ZnPc] = 10 μ M (blue solid line), absorption spectrum of ZnPc@Gel, [ZnPc] = 200 μ M (red solid line), fluorescence emission spectrum of ZnPc in 1:1 water-ethanol, [ZnPc] = 20 μ M (blue dotted line), and fluorescence emission spectrum of ZnPc@Gel, [ZnPc] = 100 μ M (red dotted line). λ_{exc} = 625 nm for both fluorescence emission measurements.

2. Supplementary Table

Table S1. Experimentally determined quantum yield of fluorescence values for ZnPc and DPP-BC in 1:1 water-ethanol solutions.

Compound	Φ_F
Zinc phthalocyanine tetrasulfonic acid (ZnPc)	0.07
DPP-BC	0.84